



TECHNICAL DATA SHEET

Page 1 of 2

HEAT RESISTING COATING MIL-P-14105

PRODUCT

A heat-resisting paint intended for use on steel..

DESCRIPTION

MIL-P-14105 a high heat resisting coating intended for use on solvent degreased and abrasive blasted steel surfaces which are subjected to temperatures as high as 1,400 Deg. F and exterior weathering.

PROPERTIES

| | | |
|-------------------|-------|-----------------|
| Colors | | Per FED-STD-595 |
| Gloss (60 Degree) | | 15 Maximum |
| Solids (Weight) | | 70% Minimum |
| Grind | | 4 Minimum |
| Viscosity | | 65 - 85 KU |

DRYING TIMES

| | |
|---------------------------|-----------------------|
| Air Dry -- Tack free..... | Within 1 Hour |
| Baking | 400 Deg. F For 1-Hour |

ADVANTAGES:

- (1). High Heat Resistance
- (2). Exterior
- (3). Durable

USES:

Mufflers, Manifolds, Heat Exchangers, Engines, and Exhaust.

MACH-DYNAMICS
3870 La Sierra Avenue, Suite 212
Riverside, CA 92505
(951) 515-3748 Fax (775) 599-4585

TECHNICAL DATA SHEET

Page 2 of 2

HEAT RESISTING COATING MIL-P-14105

APPLICATION:

Apply by brush, roller or spray methods. For brush and roll, thin with TT-T-291 Reducer at 10-15% by volume to achieve good flow and leveling. For spray application, thin with TT-X-916 Thinner at 10-15% by volume for proper atomization of the coating.

APPLICATION AND REDUCTION:

MIL-P-14105 Heat Resisting paint can be applied by brush, roller or spray. Brush small areas only. Use a short nap mohair roller with phenolic core. Avoid re-rolling! Thin with TT-T-291 (Mineral Spirits) for brush and roll and TT-X-916 (Xylene) for spray application. Spray using conventional or airless equipment with Teflon packings. Apply coating so as to produce a dry film thickness of 2.0 - 2.5 mils.

SURFACE PREPARATION:

Surfaces must be clean, dry and free of all contamination before application. Coating must be applied to degreased, bare steel. Abrasive blast to a near white finish in accordance with SSPC-SP 10.

PRECAUTIONS:

Contents are **FLAMMABLE**.
Keep away from heat and open flame.
KEEP OUT OF THE REACH OF CHILDREN.
Do not take internally.
Avoid breathing vapor or mist.
Do not use in tank or pit without proper protection.
Read Material Safety Data Sheet before use of this product.