

MACH-DYNAMICS  
3870 La Sierra Avenue, Suite 212  
Riverside, CA 92505  
(951) 515-3748 Fax (775) 599-4585



## TECHNICAL DATA SHEET

Page 1 of 1

### FAST DRY PRIMER MODIFIED ALKYD MIL-P-7962D

#### PRODUCT

A fast dry, corrosion inhibiting, spray type lacquer primer for use over metal pre-treatment wash primer MIL-C-8514C.

#### TYPICAL PROPERTIES

Colors .....	Yellow
Drying Time .....	Air Dry Hard Within 6 Minutes
Viscosity .....	13-19 Seconds (Reduced)
Fineness of Grind .....	6 Minimum
Solids By Weight .....	45% Minimum

#### APPLICATION AND REDUCTION

MIL-P-7962D is spray applied over MIL-C-8514C. It acts as a tie-coat between the pre-treatment wash primer and the topcoat of acrylic nitrocellulose or nitrocellulose lacquer. Spray one cross coat to achieve a dry film thickness of 0.3 - 0.5 mils. Thin with MIL-T-81772B Type III as needed for proper atomization, not to exceed one-pint per gallon.

#### PRECAUTIONS:

Contents are FLAMMABLE.  
Keep away from heat and open flame.  
KEEP OUT OF THE REACH OF CHILDREN.  
Do not take internally.  
Avoid breathing vapor or mist.  
Do not use in tank or pit without proper protection.  
Read Material Safety Data Sheet before use of this product.