

MACH-DYNAMICS
3870 La Sierra Avenue, Suite 212
Riverside, CA 92505
(951) 515-3748 Fax (775) 599-4585



TECHNICAL DATA SHEET

Page 1 of 1

PHENOLIC SPAR VARNISH TT-V-109C

PRODUCT

A clear, air-drying alkyd varnish for interior use.

TYPICAL PROPERTIES

Color Clear
Drying Times:
Dry Hard Within 18 Hours
Set-to-Touch Within 3 Hours
Vehicle Type Modified Alkyd
Shelf Life 1 Year From DOM
Non-Volatile (Weight) 44% Minimum

APPLICATION & REDUCTION:

TT-V-109C is normally applied by brush, roll or spray methods. Thin up to 15% by volume with Mineral Spirits as needed for proper flow and atomization.

Read MSDS before use of this product.